



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

 FON
 0049 (0) 6221 - 520 440

 FAX
 0049 (0) 6221 - 520 449

 MAIL
 INFO@CHAMAELEON-PRODUKTION.DE

 WBW
 WWW.CHAMAELEON-PRODUKTION.DE

CHAMALEON

TECHNICAL DATA SHEET

CHAMÄLEON HEAT RESISTANT SPRAY

Article number:

Intended use:

General characteristics:

26601 (Black), 26602 (Silver),

Car refinishing Product/ Preparation

High quality lacquer to treat surfaces, treated and untreated, which are exposed to very high temperatures.

Product characteristics:

- Heat resistant
- Excellent adhesion
- Resistant to petrol, chemicals and weather influences

Physical and Chemical

Contents Base VOC-content Solid content Gloss Coverage Dust dry Tack free Hardened Heat resistant

Characteristics

400 ml Silicone resin Approximately 84% w/w Approximately 16% w/w Satin matt 1,25 to 1,75 m² After 5 to 10 minutes After 10 to 15 minutes After 30 to 60 minutes (160°C) To 800°C

Usage:

Before use, carefully read the directions on the packaging and act accordingly. Chamäleon GmbH – Technical Data Sheet

CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

Pre Treatment:

Treatment:

After use:

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

 FON
 0049 (0) 6221 - 520 440

 FAX
 0049 (0) 6221 - 520 449

 MAIL
 INFO@CHAMAELEON-PRODUKTION.DE

 WEB
 WWW.CHAMAELEON-PRODUKTION.DE

CHAMALEON

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Do not apply any primer.

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the heat resistant lacquer in several thin layers. Before applying the next layer, again shake the aerosol. Allow to dry at room temperature for one hour. Then, heat for 30 to 60 minutes (160°C) in order to harden the paint layer. Smoke develops during the lacquer hardening process.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via: info@chamaeleon-produktion.de For safety information, please refer to the corresponding Safety Data Sheet.