



9600 2:1 SR **CLEARCOAT**

ET9600-SR011L ET9600-SR05 5L

Product	2K scratch resistant acrylic clearcoat. High gloss, excellent durability and UV stability.
Substrates	Apply on top of fully dry solvent and waterborne basecoats
Surface Preparation	The use of tack cloth is recommended prior application
Application Conditions	18-22°C
Mixing	2:1 by volume with Etalon hardener 9601 slow, normal, fast.
Dilution	0-5%
Pot Life	60min at 20°C
Application Viscosity	15-17 sec at 20°C Ford cup 4
Spraying Equipment	Gravity feed spray gun 1.3mm
Number of layers	2 coats
Flash off	10-12min
Coating Thickness	45-50 μm
Drying	30 min at 60° C Touch Dry: 5-6 hours at 20°C Fully Dry: 14 hours at 20°C
Drying with IR lamps	8-10 min
voc	2004/42/IIB€(840)<840
Shelf life	Clearcoat: 24months Hardener: 12months

Technical Data Sheet etalon-refinish.com