



TECHNICAL DATA SHEET No 830

SPRAY P962 ISOLATOR PRIMER

GENERAL TECHNICAL DESCRIPTION

1K air-drying isolator primer in aerosol form, based on natural components.

Prevents the lifting and isolates the old, existing paint films, which are sensitive to strong solvents.

Dries quickly.

Does not require sanding after application.

SURFACE

Any coated surface

PRETREATMENT/CLEANING OF SUBSTRATE

The surface to be coated must be dry, clean, and free of grease and other contaminants. Ensure all substrates are thoroughly cleaned and dried at every step of the preparation process.



Clean the surface with 770 NORMAL / 771 FAST ANTISIL Degreaser.

Use 2 clothes wipe on, wipe off. Always wipe cleaner off the surface as long is wet, with a clean, dry cloth. Remove dust by air blowing and a tack cloth.



P 180 / P 220



P 400, Sanding by hand, wet

PRODUCT APPLICATION:



Shake well before using:
2 - 3 min



Spray at a distance of
20 - 30 cm, thinly applied
coats



2 coats approximately
20 - 25 microns



3 - 5 min / 23°C (73°F)
Flash off time between
coats



30 - 45 min / 23°C (73°F)
Dust free
1 h / 23°C (73°F)
Full hardness



Overcoat with any HB
BODY 1K / 2K primer or
260 BODYFILLER.



After use turn bottle
upside down and spray
out a small quantity,
for the cleaning of the
nozzle

SPECIFIC GRAVITY

0.85 ± 0.02 g/cm³

SOLID CONTENT

23 ± 2% Weight

VOC (2004/42/EC)

This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 840 g/L.
2004/42/IB(e)(840)840

REMARKS

- Shake for 2 - 3 min after agitator ball has started to rattle.
- It is recommended to test on a similar surface for achieving the desired finishing result.
- Optimum operating temperature range 10 - 30°C (50 - 86°F).

STORAGE SHELF LIFE

Guaranteed shelf-life 24 months in unused original containers stored in a cool place (5 - 25°C) (41 - 77°F).



Always wear protective equipment



Follow the application instructions mentioned in this TDS

The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

AUGUST 2024