



## TECHNICAL DATA SHEET No 824

# SPRAY U951 AUTOFLEX

### GENERAL TECHNICAL DESCRIPTION

Rubber-based underbody material in aerosol form with superior adhesion.

Stone chip protection, waterproof and sound-deadening properties.

Easy to use. Fast drying.

Remains permanently elastic.

It can be overpainted with all HB BODY paint systems after drying or as wet on wet.

Optional application of an intermediate layer of HB BODY P340 PLASTOFIX, in order to enhance adhesion.

### SURFACE

Lower external parts (wheel arches, running boards, etc.) and internal areas (bonnet, trunk, etc.) of the car body

### PRETREATMENT/CLEANING OF SUBSTRATE

The surface to be coated must be dry, clean, and free of grease and other contaminants. Ensure all substrates are thoroughly cleaned and dried at every step of the preparation process.



Clean the surface with 770 NORMAL / 771 FAST ANTISIL Degreaser. Use 2 clothes wipe on, wipe off. Always wipe cleaner off the surface as long is wet, with a clean, dry cloth. Remove dust by air blowing and a tack cloth.

### PRODUCT APPLICATION:



Shake well before using:  
2 - 3 min



Spray at a distance of  
20 - 30 cm thinly applied  
coats



2 - 3 coats approximately  
200 - 300 µm



5 - 10 min / 23°C (73°F)  
Flash off time between  
coats



Dust free 10 - 15 min at  
23°C (73°F)  
Through drying 2 hours



It can be painted over  
with all HB BODY paint  
systems wet on wet or  
after drying.



After use turn bottle  
upside down and spray  
out a small quantity,  
for the cleaning of the  
nozzle

Note: For maximum adhesion,  
it is recommended to apply  
P340 PLASTOFIX, prior to  
painting. Please refer to the  
relevant Technical Data Sheet for  
application guidance.

### SPECIFIC GRAVITY

$0.80 \pm 0.03 \text{ g/cm}^3$

### SOLID CONTENT

$29 \pm 2\%$  Weight

### VOC (2004/42/EC)

This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 840 g/L. 2004/42/II(b)(840)840

### REMARKS

- Shake for 2 - 3 min after agitator ball has started to rattle.
- It is recommended to test on a similar surface for achieving the desired finishing effect.
- Optimum operating temperature range 10 - 25°C (50 - 75°F).

### STORAGE SHELF LIFE

Guaranteed shelf-life 36 months in unused original containers stored in a cool place (5 - 25°C) (41 - 77°F).



Always wear protective  
equipment



Follow the application  
instructions mentioned  
in this TDS

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.