

# **Tri Cut II** 5331, 5334

Ultimate Finish System<sup>™</sup> Tri-Cut II is designed to offer one product for three uses: 1) as a compound 2) as a swirl remover and 3) as a polisher. Tri-Cut II is safe for use on all paints.



Mix Ratio Mix Ratio: Ready to use



## Surface Prep & Application

Wash surface to be sanded with soap and water. Sand 1200-2000 grit, wet or dry until imperfections or defects are removed. Finish sand with 1500-2000 grit. Ultimate Finish System<sup>™</sup> Tri-Cut II is designed to offer 1 product for three uses. / Remove grade 1200 grit and finer sand scratches with a wool compounding pad 5200/5260 or Cutting Compound Orange Foam Pad 5272 and an air or electric buffer (1500-2000 RPM.)

/ For 1500 and finer imperfections use a Machine Polish White Foam Pad at 1200-1500  $\ensuremath{\mathsf{RPM}}$ 

/ Finish to desired gloss with a Swirl Remover Gold Foam Pad 5292 at 1000-1200 RPMs. Safe for use on all paints.

Do not apply in direct sunlight. Shake container well before use. Apply with an air or electric buffer, at speeds recommended above using the recommended pads to achieve best results. Apply enough of Tri-Cut II to the painted surface working in a 2 ft x 2 ft or panel size area. To minimize sling, spread with the compounding/polish pad before starting machine. Start machine and buff using light to medium pressure to achieve desired results. Reduce pressure as material begins to dry. Spur compound pads as necessary to assist with clean up. Finishing can be accomplished by hand or by buffer and Machine Polish White Foam Pad 5282. Apply a small amount of material, and allow material to haze over. Buff or polish to a high gloss shine. If machine applied, keep buffer moving to prevent rubbing through topcoat. After desired gloss is obtained, wash surface with soap and water and dry with a soft cloth to avoid scratching the surface.

Note: If material slings onto an adjacent panel or plastic part, remove spatter with a damp cloth as soon as possible.

Avoid contact with convertible tops, vinyl tops and plastic windows on convertibles. Note: If using a new dry pad, mist the pad with water until moist.

Note: Misting the surface with water while working with Tri-Cut II will produce a higher gloss.



#### Product Specifications

Color	White	Size (5331)	Gallon
Shelf life	3 years	(5334)	Quart

### Regulatory

Category	.Automotive rubbing or	polishing coumpound
VOC Content	.<17% by weight	



#### Limitations & Precautions

- Visit www.tat-co.com to assure use of the most current instructions and TDS on this product.
- See website (www.tat-co.com) for this document in other languages. (Vea el web site para este documento en español. Voir le site web pour ce document en français.)
- For use only by professional, trained painters. Not for sale to or use by the general public.

#### LIMITED WARRANTY

The successful performance of this product is dependent on many factors beyond our control. Results are dependent upon the skill of the operator. This product is manufactured to meet the highest level of consistency and quality for the intended use. Transtar Autobody Technologies, Inc. warrants that its products meet the specifications which it sets for them. Should this product be proven to be off-specification within shelf life as stated in this datasheet, Transtar Autobody Technologies, Inc. will, at its sole discretion, either replace the product or issue credit for the original purchase price of the product. The replacement or refund shall be the buyer's sole remedy and Transtar Autobody Technologies, Inc. and its affiliates MAKE NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, DESIGN COMPATIBILITY AND FITNESS FOR A PARTICULAR PURPOSE. LABOR OR COST OF LABOR AND OTHER INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.